

new
ker

| | | | |
|--|---------------------|-----------------------|-------------------------|
| MODEL: DOVER ANTISLIP | | | |
| BRAND: NEWKER | CODE: 181140 | COLOR: PIZARRA | DATE: 03/09/2021 |
| CERAMIC TILES CLASSIFICATION (UNE-EN-14411): Grupo Bla. Anexo G | | | |

| STANDARD | CHARACTERISTICS | TEST RESULT |
|---|---|----------------------------------|
| UNE-EN ISO 10545-4 | Breaking strength | Mín. 1300 |
| UNE-EN ISO 10545-4 | Modulus of rupture | Mín. 35 |
| UNE-EN ISO 10545-7 | Resistance to surface abrasion | |
| | Class | 3 |
| | Abrasion stage | 750 |
| UNE-EN ISO 10545-11 | Resistance to crazing | Cumple / Passed |
| UNE-EN ISO 10545-12 | Frost Resistance | Resiste / Resist |
| UNE-EN ISO 10545-14 | Resistance to staining | |
| | Fe ₂ O ₃ / Cr ₂ O ₃ | 5 |
| | Iodine / alcohol solution | 5 |
| | Light oil | 5 |
| UNE-EN ISO 10545-13 | Chemical Resistance | |
| | Household chemicals | Mín. Ga |
| | Swimming pool salts | Mín. Ga |
| | Citric Acid | Mín. Gla |
| | Lactic Acid | Mín. Gla |
| | Hydrochloric Acid low concentrations | Mín. GLA |
| | Hydrochloric Acid high concentrations | Mín. GHA |
| | Potassium Hydroxide low concentrations | Mín. GLA |
| Potassium Hydroxide high concentrations | Mín. GHA | |
| Dimension (mm) | 310,2x310,2 | |
| | | Thickness (mm) 8.6 |
| Slipperness | C3 | Water absorption E < 0,5% |

new
ker

NUEVA CERÁMICA NEWKER CA SL
B-12880357
C/ Sta. Magdalena de Pulpis, 10
12006 - CASTELLÓN (SPAIN)