

new
ker

| | | | |
|---|---------------------|---------------------|-------------------------|
| MODEL: CONTACT DECOR | | | |
| BRAND: NEWKER | CODE: 176207 | COLOR: WHITE | DATE: 10/30/2020 |
| CERAMIC TILES CLASSIFICATION (UNE-EN-14411): Grupo BIII. Anexo L | | | |

| STANDARD | CHARACTERISTICS | TEST RESULT |
|---|---|---------------------------------|
| UNE-EN ISO 10545-4 | Breaking strength | Mín. 700 |
| UNE-EN ISO 10545-4 | Modulus of rupture | Mín. 16 |
| UNE-EN ISO 10545-7 | Resistance to surface abrasion | |
| | Class | - |
| | Abrasion stage | - |
| UNE-EN ISO 10545-11 | Resistance to crazing | Cumple / Passed |
| UNE-EN ISO 10545-12 | Frost Resistance | - |
| UNE-EN ISO 10545-14 | Resistance to staining | |
| | Fe ₂ O ₃ / Cr ₂ O ₃ | 5 |
| | Iodine / alcohol solution | 5 |
| | Light oil | 5 |
| UNE-EN ISO 10545-13 | Chemical Resistance | |
| | Household chemicals | Cumple /Passed |
| | Swimming pool salts | Cumple / Passed |
| | Citric Acid | Mín. Gla |
| | Lactic Acid | Mín. Gla |
| | Hydrochloric Acid low concentrations | Mín. GLA |
| | Hydrochloric Acid high concentrations | Mín. GHA |
| | Potassium Hydroxide low concentrations | Mín. GLA |
| Potassium Hydroxide high concentrations | Mín. GHA | |
| Dimension (mm) | 298,0x898,0 | Thickness (mm) 10.6 |
| Slipperness | | Water absorption E > 10% |

new
ker Nueva Cerámica NEWKER
Costa de Azahar S.L.
B-12880357 * C/Grecia 63
12006 - Castellón (Spain)