

new
ker

| | | | |
|--|---------------------|---------------------|-------------------------|
| MODEL: CITY | | | |
| BRAND: NEWKER | CODE: 183125 | COLOR: TAUPE | DATE: 10/20/2020 |
| CERAMIC TILES CLASSIFICATION (UNE-EN-14411): Grupo Bla. Anexo G | | | |

| STANDARD | CHARACTERISTICS | TEST RESULT | | |
|---|---|------------------|-------------------------|----------|
| UNE-EN ISO 10545-4 | Breaking strength | Mín. 1300 | | |
| UNE-EN ISO 10545-4 | Modulus of rupture | Mín. 35 | | |
| UNE-EN ISO 10545-7 | Resistance to surface abrasion | | | |
| | Class | 2 | | |
| | Abrasion stage | - | | |
| UNE-EN ISO 10545-11 | Resistance to crazing | Cumple / Passed | | |
| UNE-EN ISO 10545-12 | Frost Resistance | Resiste / Resist | | |
| UNE-EN ISO 10545-14 | Resistance to staining | | | |
| | Fe ₂ O ₃ / Cr ₂ O ₃ | Cumple / Passed | | |
| | Iodine / alcohol solution | Cumple / Passed | | |
| | Light oil | Cumple / Passed | | |
| UNE-EN ISO 10545-13 | Chemical Resistance | | | |
| | Household chemicals | Cumple /Passed | | |
| | Swimming pool salts | Cumple / Passed | | |
| | Citric Acid | Mín. Glb | | |
| | Lactic Acid | Mín. Glb | | |
| | Hydrochloric Acid low concentrations | Mín. GLB | | |
| | Hydrochloric Acid high concentrations | Mín. GHB | | |
| | Potassium Hydroxide low concentrations | Mín. GLB | | |
| Potassium Hydroxide high concentrations | Mín. GHB | | | |
| Dimension (mm) | 600x600 | | Thickness (mm) | 10.0 |
| Slipperness | C1 | | Water absorption | E < 0,5% |

new
ker Nueva Cerámica NEWKER
Costa de Azahar S.L.
B-12880357 * C/Gracia 63
12006 - Castellón (Spain)